## **Jampilen RP340N** polymer.corRandom Copolymer ner.com

panizahun

olymer.co

ymer.com



paniza **Description:** 

"Jampilen RP340N" is a polypropylene random copolymer which features extremely high flow properties, excellent transparency, high gloss and exhibits good antistatic properties. "Jampilen RP340N" is mainly designed for transparent thin-walled packaging where clarity is of utmost importance. In many of these applications, "Jampilen PP340NI" housewares and quality packaging applications. It is an since it can match the optical properties whilst adding low weight, low odor transfer, chemical resistance and impact panizapolymer.com strength.

Injection molding Extrusion (Sheet)

High flow properties Excellent transparency High gloss Good antistatic properties Random copolymer

**Typical Applications:** 

**Processing Method:** 

**Features:** 

panizapolymer Injection molded containers and thin-walled packaging Clear containers 72 Household articles Packaging for food, cosmetics and pharmaceutical products Lids, caps and closures Coextrusion with other polypropylene resins to produce multilayer sheet for thermoforming trays for fresh pasta and panizapolym Sports, Leisure and toys

anizapolymer.com **Approval:** 

Food

	TYPICAL PROPERTIES	VALUE	UNIT	METHOD
	Physical		non	
	Melt Flow Rate (230 °C, 2.16kg)	11	g/10min	ASTM D1238
	Density	0.9	g/cm <sup>3</sup>	ASTM D1505
03	Mechanical	AUIZON		nant
	Flexural Modulus	1050	MPa	ASTM D790
	Tensile Strength at Yield	28	MPa	ASTM D638
	Tensile Elongation at Yield	12	%	ASTM D638
	Izod Impact Strength (notched) at 23 °C	85	J/m	ASTM D256
Johnen.	Rockwell Hardness	94	R Scale	ASTM D785
	Thermal JZ2P	nizap		
	Vicat softening point (10N)	128	°C	ASTM D1525
	H.D.T. (0.46 Mpa)	83	°C	ASTM D648
	Accelerated oven ageing in air at 150 °C	360	hours	ASTM D3012
	Optical			
	Haze $(1 \text{ mm}) \propto CO^{111}$	9	%	ASTM D1003
	Gloss (60°)	85	IME	ASTM D2457
	4 <sup>th</sup> Floor, No. 68, Taban St., Africa Blvd., Tehran, Iran. Tel: +9821-84286, Fax: +9821-88879811	nizapor	7	in

Email: info@jppc.ir www.jppc.ir

Luner.com

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.